

Q.MAXX-G2 345-360

ENDURING HIGH PERFORMANCE







Higher yield per surface area, lower BOS costs, higher power classes, and an efficiency rate of up to 20.4%.



ப் ப

INNOVATIVE ALL-WEATHER TECHNOLOGY Optimal yields, whatever the weather with excellent low-light and temperature behaviour.



ENDURING HIGH PERFORMANCE

Long-term yield security with Anti LID Technology, Hot-Spot Protect and Traceable Quality Tra.Q™.



EXTREME WEATHER RATING

High-tech aluminium alloy frame, certified for high snow (5400 Pa) and wind loads (4000 Pa).



A RELIABLE INVESTMENT

Inclusive 15-year product warranty and 25-year linear performance warranty¹.



STATE OF THE ART MODULE TECHNOLOGY

Q.ANTUM DUO combines cutting edge cell separation and innovative 12-busbar design with Q.ANTUM Technology.

¹ See data sheet on rear for further information.

THE IDEAL SOLUTION FOR:






Rooftop arrays on commercial/industrial buildings



MECHANICAL SPECIFICATION

Format	1740 mm × 1030 mm × 32 mm (including frame)
Weight	19.9 kg
Front Cover	3.2 mm thermally pre-stressed glass with anti-reflection technology
Back Cover	Composite film
Frame	Black anodised aluminium
Cell	6 × 20 monocrystalline Q.ANTUM solar half cells
Junction box	53-101 mm × 32-60 mm × 15-18 mm Protection class IP67, with bypass diodes
Cable	4mm² Solar cable; (+) ≥1150mm, (-) ≥1150mm
Connector	Stäubli MC4; IP68




ELECTRICAL CHARACTERISTICS

PO	WER CLASS			345	350	355	360
MIN	IIMUM PERFORMANCE AT STANDA	RD TEST CONDITIO	NS, STC ¹ (PO)	VER TOLERANCE +5 W /	-0W)		
Minimum	Power at MPP ¹	P _{MPP}	[W]	345	350	355	360
	Short Circuit Current ¹	I _{sc}	[A]	10.68	10.74	10.79	10.84
	Open Circuit Voltage ¹	V _{oc}	[V]	40.45	40.70	40.95	41.19
	Current at MPP	I _{MPP}	[A]	10.17	10.22	10.28	10.33
	Voltage at MPP	V _{MPP}	[V]	33.92	34.24	34.55	34.85
	Efficiency1	η	[%]	≥19.3	≥19.5	≥19.8	≥20.1
MIN	JIMUM PERFORMANCE AT NORMAL	OPERATING CON	DITIONS, NMC) T ²			
	Power at MPP	P _{MPP}	[W]	258.4	262.1	265.9	269.6
Minimum	Short Circuit Current	I _{sc}	[A]	8.61	8.65	8.69	8.74
	Open Circuit Voltage	V _{oc}	[V]	38.14	38.38	38.61	38.85
	Current at MPP	I _{MPP}	[A]	8.00	8.05	8.09	8.13
	Voltage at MPP	V _{MPP}	[V]	32.28	32.57	32.87	33.16


¹Measurement tolerances P_{MPP} ±3%; I_{Sci} V_{oc} ±5% at STC: 1000 W/m², 25±2°C, AM 1.5 according to IEC 60904-3 • 2800 W/m², NMOT, spectrum AM 1.5

Q CELLS PERFORMANCE WARRANTY



At least 98% of nominal power during first year. Thereafter max. 0.54% degradation per year. At least 93.1% of nominal power up to 10 years. At least 85% of nominal power up to 25 years.

All data within measurement tolerances. Full warranties in accordance with the warranty terms of the Q CELLS sales organisation of your respective country.



Typical module performance under low irradiance conditions in comparison to STC conditions (25 $^{\circ}\text{C},$ 1000W/m²).

TEMPERATURE COEFFICIENTS

Temperature Coefficient of Isc	nperature Coefficient of I _{sc} a [%/K] +0.04 Temperature Coefficient of V _{oc}		ß	[%/K]	_0.27		
Temperature Oberncient of I _{sc}	u	[/0/ K]	+0.04	remperature obernolent of voc	P	[/0/ []	-0.27
Temperature Coefficient of $P_{_{\text{MPP}}}$	γ	[%/K]	-0.36	Nominal Module Operating Temperature	NMOT	[°C]	43±3

PROPERTIES FOR SYSTEM DESIGN

Maximum System Voltage	V_{SYS}	[V]	1000	PV module classification	Class II
Maximum Reverse Current	I _R	[A]	20	Fire Rating based on ANSI / UL 61730	C/TYPE 2
Max. Design Load, Push / Pull		[Pa]	3600/2660	Permitted Module Temperature	-40°C - +85°C
Max. Test Load, Push / Pull		[Pa]	5400/4000	on Continuous Duty	

QUALIFICATIONS AND CERTIFICATES

PACKAGING INFORMATION



Note: Installation instructions must be followed. See the installation and operating manual or contact our technical service department for further information on approved installation and use of this product.

Made in China

Hanwha Q CELLS Australia Pty Ltd

Suite 1, Level 1, 15 Blue Street, North Sydney, NSW 2060, Australia | TEL +61 (0)2 9016 3033 | FAX +61 (0)2 9016 3032 | EMAIL q-cells-australia@q-cells.com | WEB www.q-cells.com/au

